

Repairing a Chipped Disc

01 - Before shaping a disc with chips



02 - Using a painter's tape at chips (wire brush with liquid soap, rinse).



Follow by 100x stirred epoxy after tape. Clear. Note tip does not have a mixer (hard to reuse on mixing tip). Mark cap to replace after use. Stir 100 times for best mixture. Let set 24 hours in spite of the five minute set the say.



I use a Qtip into chips. It says 5 minutes..... Give it 24 hrs. More later after set and sand.



Followed by my spinner sanding off extra epoxy after epoxy sets.



Sanding blocks, finer grades not shown



After repairing with epoxy I have never chipped again at an epoxy site.



Rust-Oleum JD yellow. John Deere

The red is Gloss Regal Red. Recoat within 29 minutes. Wait minimum 48 hours.
When painting the tops mask areas. Before masking sand the top using 80, 100, 120, 150, 180, 220 to remove scratches and to help bonding.